

Technical Data Sheet

Product Name	
Full Product Name	Jet Acrylic Black
Type of Product	1K acrylic topcoat
Description	Concept Jet Acrylic Black is a high gloss and high opacity 1K acrylic black topcoat, designed for automotive components. It is characterized by its excellent adhesion and long term durability.

Products						
Product Name	Volume Solids	Weight Solids	Density		VOC	
	%	%	g/mL	lbs/US gal	g/L	lbs/US gal
Jet Acrylic Black	26.7	32.8	0.943	7.87	633.5	5.29
Acrylic Thinner	0.0	0.0	0.840	7.01	839.8	7.01
Retarder Thinner	0.0	0.0	0.884	7.38	884.0	7.38

Properties
<ul style="list-style-type: none"> • High gloss
<ul style="list-style-type: none"> • High opacity

Substrates
<ul style="list-style-type: none"> • Concept Acrylic Primer
<ul style="list-style-type: none"> • Concept Two in One Primer
<ul style="list-style-type: none"> • Concept 1K Etch Primer
<ul style="list-style-type: none"> • Concept Universal 4000 Primer
<ul style="list-style-type: none"> • Sound existing surfaces, except for unstable surfaces such as nitrocellulose or enamels.

Substrate Preparation



All Substrates

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.

Product Preparation



Reducer

100% (v/v) Concept Acrylic Thinner
5-10% Concept Retarder Thinner, if required (to minimise blooming)



Pot life @ 25°C (77°F)

N/A



Spray viscosity @ 25°C (77°F)

BSB 4 Cup	18-19 s
Ford 4 Cup	16-17 s



Spray equipment

Gun type	Fluid tip	Spray pressure	Spray Distance
Gravity feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
Suction feed	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
HVLP	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch



Number of coats

3-4	Apply one coat followed by two or three even full coats. Avoid heavy wet coats.
-----	---------------------------------------------------------------------------------



DFT Recommended

40-50 µm
1.6-2.0 mils



Flash off time @ 25°C (77°F)

5 min between coats



Drying

Air Dry @ 25°C (77°F)	40-60 min
---------------------------------	-----------





Polishing

Sand with P1200 before polishing

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Technical Data Sheet

Remarks	
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh-out of the components.
	Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Equipment Cleaning	
Use recommended Concept Paints cleaner	

Dry Film Properties	
After 7 days drying, <u>when compared to similar technology products.</u>	
Gloss	High
Adhesion	Excellent
Durability	Excellent

Product Data	
Colour	Black
Theoretical Coverage	Approx. 5.0 m ² /L (205 ft ² /US gal) @ recommended DFT
Shelf Life	36 months in an unopened container at room temperature, away from sunlight.

Product Packaging			
Product Code 1	Product Code 2	Product Name	Package Size
A06C/JETB	3567000	Jet Acrylic Black	1L, 4L, 20L
A08C/ACR	8029200	Acrylic Thinner	1L, 4L, 20L, 60L
A08C/RET	8109200	Retarder Thinner	1L, 4L, 20L

Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints
26-30 Charles Street
St Marys NSW 2760
Sydney, Australia

ph. +61 (2) 9673 2555
fax. +61 (2) 9623 1918
info@conceptpaints.com.au
www.conceptpaints.com.au